

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Original): A curable resin composition comprising a (meth)acrylate monomer, an organic peroxide, a decomposition accelerator for the organic peroxide, and an inorganic filler, wherein the inorganic filler has a particle size distribution such that it has peak diameters at least in the respective regions of from 3 to 10  $\mu\text{m}$  and from 30 to 70  $\mu\text{m}$ , and the mode diameter is from 30 to 70  $\mu\text{m}$  and the median diameter is from 5 to 40  $\mu\text{m}$ .

Claim 2 (Original): A curable resin composition comprising a (meth)acrylate monomer, an organic peroxide, a decomposition accelerator for the organic peroxide and an inorganic filler, wherein the inorganic filler has a particle size distribution such that it has peak diameters at least in the respective regions of from 0.2 to 1.5  $\mu\text{m}$ , from 3 to 10  $\mu\text{m}$  and from 30 to 70  $\mu\text{m}$ , and the mode diameter is from 30 to 70  $\mu\text{m}$  and the median diameter is from 5 to 40  $\mu\text{m}$ .

Claim 3 (Currently Amended): The curable resin composition according to Claim 1 or 2, which comprises from 0.5 to 10 parts by mass of the organic peroxide, from 0.1 to 10 parts by mass of the decomposition accelerator and from 100 to 1,500 parts by mass of the inorganic filler, respectively, per 100 parts by mass of the (meth)acrylate monomer.

Claim 4 (Original): The curable resin composition according to Claim 1, which further contains a drying oil.

Claim 5 (Original): The curable resin composition according to Claim 2, which further contains a drying oil.

Claim 6 (Currently Amended): The curable resin composition according to Claim 4 ~~or 5~~, which comprises from 1 to 30 parts by mass of the drying oil, from 0.5 to 10 parts by mass of the organic peroxide, from 0.1 to 10 parts by mass of the decomposition accelerator and from 100 to 1,500 parts by mass of the inorganic filler, respectively, per 100 parts by mass of the (meth)acrylate monomer.

Claim 7 (Currently Amended): The curable resin composition according to ~~any one of Claims 1 to 6~~ Claim 1, wherein the inorganic filler is spherical alumina.

Claim 8 (Currently Amended): A cured product made of the curable resin composition as defined in ~~any one of Claims 1 to 7~~ Claim 1.

Claim 9 (Currently Amended): A potting material made of the curable resin composition as defined in ~~any one of Claims 1 to 7~~ Claim 1.

Claim 10 (Currently Amended): An adhesive made of the curable resin composition as defined in ~~any one of Claims 1 to 7~~ Claim 1.